

BLANCO TERA GRANITE



	RESULTS
Petrographic Examination (UNE-EN 12407:2007)	Granite
Water Absorption (UNE-EN 13755:2007)	Mean Value 0,3%
Apparent Density and Open Porosity (UNE-EN 1936:2007)	Apparent Density 2.589 Kg / m3 Open Porosity 0,9 %
Frost Resistance (12 cycles) (UNE-EN 12371:2011)	Flexural Strength 4,8 cm2 / 50 cm2
Flexural Strength (UNE-EN 12372:2007)	Flexural Strength 10%
Breaking Load at Dowel Hole (UNE-EN 13364:2002)	Breaking Load 1400 N
Water Absorption by Capillarity (UNE-EN 1925:1999)	Coefficients 9,23 g / m2s0,5